

Fabrication in Space – What Materials are Needed?

In order to sustain life on the moon, and especially on Mars, the inhabitants must be selfsufficient. As on Earth, electronic and mechanical systems will break down and must be repaired. It is not realistic to "send" parts to the moon or Mars in an effort to replace failed ones or have spares for all components. It will be important to have spares on hand and even better would be to have the capability to fabricate parts in situ. The In Situ Fabrication and Repair (ISFR) team is working to develop the Arcam Electron Beam Melting (EBM) machine as the manufacturing process that will have the capability to produce repair parts, as well as new designs, and tooling on the lunar surface and eventually on Mars.

What materials will be available for the inhabitants to use? What materials would be most useful? The EBM process is versatile and can handle a multitude of materials. These include titanium, stainless steels, aluminums, inconels, and copper alloys. Research has shown what parts have failed during past space missions and this data has been compiled and assessed. The EBM machine is fully capable of processing these materials of choice. Additionally, the long-term goal is to use the lunar regolith as a viable feedstock. Preliminary work has been performed to assess the feasibility of using raw lunar regolith as a material source or use a binder combined with the regolith to achieve a good melt.

Abstract for Arcam User's Group Meeting Simi Valley, California November 14-15, 2007

Jim Good, Teledyne Brown Engineering Jim.good@tbe.com

Marshall Space Flight Center

Fabrication in Space What Materials are Needed?

Arcam User's Group Meeting Simi Valley, California November 14-15, 2007

Presenter: Jim Good / Teledyne Brown Engineering for NASA - Marshall Space Flight Center jim.good@tbe.com 256-726-1199

Fabrication Technology Development Overview

AGENDA

History

In Situ Fabrication and Repair (ISFR)
Why is ISFR Technology Needed?
ISFR Scope
Fabrication Technologies External Customers
Historical Failure Analysis
Material Set Definition
Material Feasibility Studies of Selected Materials
Special Studies – Lunar Regolith Fabrication
The Mission at Hand...

A Little Bit of History.....

Exploration Vision for NASA

President George Bush on January 14, 2004 issued his vision for U.S. Space Exploration:

Extend human presence across the solar system, starting with a human return to the moon by 2020, in preparation for human exploration of Mars and other destinations

In Situ Fabrication and Repair (ISFR)

The In Situ Fabrication and Repair (ISFR) element, as part of the Human System Research & Technology Development Program, was established as NASA moved to align with the President's vision.

The ISFR Element has focused on 2 primary areas:

- Fabrication Technologies
- Repair and Nondestructive Evaluation (NDE)

Why is ISFR Technology Needed?

- Longer duration missions without near access to Earth will require increased maintainability of systems
- <u>Component degradation and failure is inevitable</u>
- The Space Architect has identified sparing as a principal issue for reducing the mass required for long duration exploration missions
- It would not be practical to carry a complete spare parts and tools inventory, nor would an extensive collection of spares necessarily fulfill every emergency need
- Fabrication of new tools in situ to cover unforeseen needs will significantly mitigate risk
- Fabrication equipment used for components, parts, and tools can also be used for electronic or biological applications (with proper cleanliness and sterility observed)
- Humans living in reduced gravity and harsh environment for extended periods of time must be able to act autonomously for their survival
- Additional potential for crew injuries requires new medical techniques
- As the distance between Mission location and Earth increases, risk increases, and advanced tool suite will help mitigate some of these
- To keep Jim Good Employed!

In Situ Fabrication & Repair (ISFR) Scope

Fabrication Technologies

capabilities with the following emphases:



- Net shape parts, tools, components with specified geometrical tolerances, strength, and integrity
- Autonomous operation, with the exception of feedstock change-out, normal maintenance, and parts removal
- · Integral non-destructive evaluation functions
- · Concentration on metal materials
- Replacement parts, unforeseen tools, advanced-life-support parts, habitat fittings





Repair & Non-Destructive Evaluation (NDE)


capabilities with the following emphases:

- Multi-material repair by joining, patching, or filling of metals, composites, or plastics
- · Handheld soldering tool
- Portable or robotic metaljoining systems
- Portable or handheld NDE systems to perform QA and safety inspections
- Chemical analysis or closed-loop control of in situ processes

l'echnologi abrication



• Initially, the Fabrication Technology team concentrated on In Situ Fabrication



Early Concept for a Multi- Material Fabricator Ground Unit (Processing, Metals, Plastics, Ceramics, & Composites)

In Situ Fabrication & Repair (ISFR) Scope

- Currently, the ISFR team has concentrated on near-term applications
 - NASA budget focused on new vehicles
 - Fab Technologies need validation and credibility



Lower Barrymount



Hydrogen Pump Discharge for **Ascent/Descent Engine**





GRCOP-84 Test Samples & Development Build












Cylinder Block

.....

ECLSS Subscale Test Component

Titanium Tensile Specimens



Historical Failure Analysis

First phase of the Failure History Analysis has been completed

• Investigated recent failures in space and space-like equipment.

Purpose of the Analysis:

- Initiated in response to BCPR requirements for risk mitigation by reducing the number of unrecoverable failures.
- Investigate existing failure data to determine the percentage of failures that ISFR technologies would be able to either prevent or repair.

Analysis Approach :


- First phase of the Analysis activity focused on ISS Problem Report and Corrective Action (PRACA) database, primarily due to applicability, availability, and ease of querying the data.
- Analysis was directed towards identification of problems resulting from broken or damaged components.
- Identified equipment which are high risk candidates for failure on a mission.
- Follow-on Analysis will occur



Historical Failure Analysis

Summary of Results :

- Phase 1 data concentrated on Environmental Control and Life Support System (ECLSS) and Crew Health Care System (CHeCS)
- Significant percentage of ISS failures could be addressed with ISFR Technologies-Fabrication and Repair/NDE
- · Composed a list of materials involved in the failures.
- Charted highest-use materials for the failures.
- This determined the material set of interest for ISFR



Material Set Definition

NASA

The main goal of Fabrication Technologies is to provide rapid manufacturing of parts and tools via a quality-controlled approach that may be a single process or a hybrid mix of additive and subtractive processes.

The set of materials needed to manufacture parts and tools was determined by:

- Failure Analysis Results
- Analysis of Material Identification and Usage Lists (MIUL) of Space Station and Space Shuttle Mid-Deck Payloads
- TIMs with flight-hardware development programs at NASA/MSFC

Material	Alloy				
Aluminum	6061				
Aluminum	7075				
Titanium	Ti-6Al-4V				
Stainless Steel	316				
Stainless Steel	17-4PH				
Inconel	625				
Inconel	718				

Metallic Material Set Targeted for Fabrication Technology Development

Marshall Space Flight Center contracted Arcam to perform feasibility studies on selected materials that are of interest in the aerospace industry, as well as the military.

• The deliverable consisted of a final report concluding whether the material is a viable candidate for EBM fabrication. Additionally, the "theme" is provided for use in future development efforts.

Material	Comments
316L	Feasibility Study Performed by Arcam
IN 625	Feasibility Study Performed by Arcam
IN 718	Feasibility Study Performed by Arcam
17-4PH	Feasibility Study Performed by Arcam
Al 6061	Feasibility Study Performed by Arcam
Al 7075	Development Effort Currently Underway by NC State University
AL 2024	Development Effort Currently Underway by NC State University
Ti-6Al-4V	Powder Available through Arcam
Ti-6Al-4V ELI	Powder Available through Arcam
CoCr	Powder Available through Arcam
GRCOP-84	Feasibility Study Performed by NC State University

Materials Available and Under Development for the EBM Process

316L Stainless Steel


The feasibility study shows that stainless steel 316L powder behaves well in the Arcam EBM process. The powder has good melting properties and the process has proven stable over several hundreds of melting layers.


Tensile Properties

	Wrought 316L	Vertical Tensile Bars		Horizontal Tensile Bars			
Tensile Properties (RT)	(ASM Handbook)	060510	060512	060515	060510	060512	060515
Tensile Strength, Ult, Mpa	450-620	539	549	554	384	255	239
Tensile Strength, Yld, MPa (@2% offset)	170-310	304	290	287	254	209	190
Elongation at Break, %	30-40	34.5	40.0	34.5	14.5	37	37
Reduction of Area, %	40-50	41	42	40	11	4	3

Microstructure and Porosity

- No macroscopic porosity in the build material, neither powderinduced nor process-induced
- The material is anisotropic. A layered structure composed of remaining weld lines are seen in the Z cross-sections. The grain structure is austenitic and elongated in the Z direction, resembling columnar grain growth.
- Vertical intergranular cracks are seen in the samples. The crack lengths are up to a few millimeters in the Z direction.
- Small particles are seen in some grain boundaries. This might be segregated material leading to grain-boundary embrittlement.





17-4 PH Stainless Steel


The feasibility study shows that 17-4 PH metal powder behaves well in the Arcam EBM process. The powder has good melting properties and the process has proven stable over several hundreds of melting layers.


Tensile Properties

T. 'I D. (' (DT))	Wrought 17-4 PH	Horizontal 7	Fensile Bars	Vertical Tensile Bars		
Tensile Properties (RT)	(ASM Handbook)	R4-060602	R4-060607	R4-060602	R4-060607	
Tensile Strength, Ult, Mpa	795-1310	1274, 1293	477, 1251	1259, 1267	1174, 577	
Tensile Strength, Yld, MPa (@2% offset)	515-1170	428, 488	322, 426	473, 495	428, 338	
Elongation at Break, %	10-18	12.5, 11.5	1.5, 5.5	14.5, 15.5	13, 3	
Reduction of Area, %	35-55	30, 33	3.9	40, 48	24, 5	

Microstructure and Porosity

- There is no visible spherical porosity in the build material.
- There are no visible macroscopic defects (voids, cavities, cracks, inclusions,...)
- The built 17-4 PH material is anisotropic. A layered structure composed of remaining weld lines are seen in the Z cross sections. The grain structure is elongated in the Z direction.
- The material is martensitic with quite small grain size. A coarser microstructure is seen when cooled faster down to room temperature.
- Small dark particles have segregated to the grain boundaries. These might be particles associated with precipitation-hardening.





Inconel 625

The feasibility study shows that IN 625 metal powder can be used in the Arcam EBM process. The powder has good melting properties and the process has proven stable over several hundreds of melting layers.

Tensile Properties


Tensile Properties (RT)	Wrought IN 625 1)	Cast IN 625 2)	051207	060428	060502	060503
Tensile Strength, Ult, Mpa	930	710	702, 673	773, 780	784, 789	746
Tensile Strength, Yld, MPa (@2% offset)	517	350	349, 355	423, 424	426, 430	395
Elongation at Break, %	42.5	48	34.5, 27	41.4, 44.5	38.5, 40	44.5
Reduction of Area, %	Not specified	Not specified	37, 28	59,66	41,66	61

1) Annealed - ASM Handbook, 10th Ed., Vol. 1, P. 984

1) Cast - ASM Handbook, 10th Ed., Vol. 1, P. 958-960

Microstructure and Porosity

- There is no visible spherical porosity in the build material using the P227 powder. Spherical pores are seen in the build material using the P175 powder.
- There are no visible macroscopic defects (voids, cavities, cracks, inclusions,...)
- The built IN 625 material is anisotropic. A layered structure composed of remaining weld lines are seen all over the cross sections. The layered structure gradually fades from the top to the bottom of the builds, indicating a thermal ageing of the material.
- The microstructure is predominantly aligned parallel to the Z direction, resembling directional solidification (columnar grain growth).



Build Direction

Layer Direction





→ Layer Direction





Inconel 718

The feasibility study shows that IN 718 metal powder can be used in the Arcam EBM process. The powder has good melting properties and the process has proven stable over several hundreds of melting layers, provided that the build temperature is kept very high, close to 1000°C.


Tensile Properties

Tanaila Dranartias (DT)	Horizontal Tensile Bars			Vertical Tensile Bars			
Tensile Properties (RT)	R	4-06091	9	R4-060919			
Tensile Strength, Ult, Mpa	1077	1074	1030	675	908	950	
Tensile Strength, Yld, MPa (@2% offset)	832	840	794	518	701	787	
Elongation at Break, %	23	23	18.5	7	5.5	5.5	
Reduction of Area, %	28	32	15	38	11	12	

Microstructure and Porosity

- The grain size is fine and anisotropic. The grains are very elongated in the build direction, resembling directional solidification (columnar grain growth).
- A layered structure showing remaining weld lines are seen all over the cross sections. The layered structure gradually fades from the top to the bottom of the builds, including a slow thermal ageing of the material.
- There are areas of poor interfusion between layers, indicating that further process optimization and/or better vacuum are needed.
- The material appears dense when inspected in a polished condition.





Aluminum 6061

The feasibility study shows that that are three basic problems to be solved with the AL 6061 from metal powder, using the Arcam EBM machine. The powder distribution system does not work well for the tested powder. Too much magnesium is evaporated. Large vertical cracks, probably hot cracks, exist in the built material.


Tensile Properties

The built material broke during machining. The fracture surfaces indicate that the machining failure is due to large vertical cracks in the material.


Microstructure and Porosity

• Etched cross sections in the build direction (Z) and in the layer direction (XY) are not of good quality and show a pronounced columnar grain growth.

•The grains are coarse and very elongated in the build direction. It is likely that the vertical cracks have propagated along the vertical grain boundaries.



Layer Direction



Special Studies – Lunar Regolith Fabrication

• In Situ Resource Utilization (ISRU)


The ISRU works to establish, evaluate and assess the in situ resources available on the moon and Mars and the technologies needed to utilize and exploit these resources.

Marshall Space Flight Center (MSFC) is playing a significant role involving the Lunar Regolith

- Defining the Requirements for the production of lunar regolith simulant
- Overseeing the production of several tons of lunar simulant


The ISFR team seeks to determine the feasibility of lunar regolith as a viable feedstock for the fabrication of component parts.






North Carolina State University has performed a "quick-look" assessment using the EBM machine and a small portion of lunar simulant, as provided by MSFC. Arcam has a small volume of simulant and will perform a similar study with a simulant that represents a different recipe.

The Mission At Hand...



abrication Technologies

Fabrication, Assembly, and Repair Module



For more information:

Carole McLemore, Project Manager In Situ Fabrication/In Situ Resource Utilization (ISFR/ISRU)

carole.a.mclemore@nasa.gov

(256)544-2314